

Brand Name	% Al	% Si	Melting range
TBW Harasil NC 12	88	12	580 °C
Brand Name	% Zn	% Al	Melting range
TBW Zinal 4	98	2	440 - 460°C
TBW Zinal 30NCS	85	15	420 - 450°C
Brand Name	% Ag	Others	Melting range
TBW 2040	40	Cu 19% Zn 21% Cd 20%	592 - 630°C
TBW 5034	34	Cu 36% Zn 27% Sn 3%	630 - 730°C
TBW 5038	38	Cu 31% Zn 28.8% Sn 2.2%	660 - 700°C
TBW 5040	40	Cu 30% Zn 28% Sn 2%	650 - 710°C
TBW 5045	45	Cu 27% Zn 25% Sn 3%	640 - 680°C
TBW 5056	56	Cu 22.5% Zn 16.5% Sn 5%	620 - 655°C



### APPLICATIONS :

- Copper and steel brazing
- Automotive air conditioning
- household equipment
- Recovering and maintenance of treated steel.
- Spectacle trade
- Jewelry
- Precise brazing

**RODS DIAMETER (A) :** 1,2 mm – 5,0 mm x 500mm—1000mm

**WIRE DIAMETER (A) :** 0.8 mm – 3,0 mm

**INSIDE DIAMETER (B) :** 5mm— 20mm

**NOTE :** other alloys, fluxes, customized wire sizes and pre-forms on demand.